

Technical Datasheet

DESCRIPTION

Luran SAN C is an injection molding grade of SAN with medium impact strength and high flow.

FEATURES

- Transparent
- High flow
- Medium impact strength

APPLICATIONS

- Home appliances
- Electrical and electronics
- General Injection Molding Application

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	23
Mechanical Properties			
Charpy Unnotched, 23° C	ISO 179	kJ/m ²	-
Tensile Stress at Yield, 23° C	ISO 527	MPa	68
Tensile Modulus	ISO 527	MPa	-
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50°C/h, 50N)	ISO 306	°C	-
Vicat Softening Temperature, B/2 (120°C/h, 50N)	ASTM D 1525	°C	104
Other Properties			
Density	ISO 1183	kg/m ³	-

Typical values for uncolored products

SUPPLY FORM

Luran is delivered in the form of cylindrical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm³. Values may differ for special grades. Standard Packaging unit: 25 kg paper bag. In addition, delivery in larger units of up to 1000 kg (IBC = Intermediate Bulk Container) or silo trucks can be arranged. In dry areas with normal temperature control, Luran pellets can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Luran absorbs moisture, but this can be removed by drying.

PRODUCT SAFETY

Given appropriate processing of the products and suitable ventilation measures in production areas, no adverse effects on the health of process operators have been found. Workplace limits for styrene and acrylonitrile, as given in the national listings applicable, must be adhered to. The values currently applicable in Germany under TRGS 900 (issue of October, 2002) for maximum workplace concentrations are as follows. Styrene: $20 \text{ ml/m}^3 = 86 \text{ mg/m}^3$; acrylonitrile: $3 \text{ ml/m}^3 = 7 \text{ mg/m}^3$. Appendix I of Directive 67/548/EWG and TRGS 905 (issue of October, 2002) classify acrylonitrile in carcinogenic category II (substances which should be regarded as carcinogenic in humans).

Experience has shown that during appropriate processing of Luran with suitable ventilation the values obtained are well below the limits mentioned above. TRGS 402 (Germany) can be used for determining and assessing the concentrations of hazardous substances in the air within working areas. Inhalation of gaseous degradation products, such as those which may arise on severe overheating of the material or during pumped evacuation, must be avoided. Further information can be found in our Luran safety data sheets.

DISCLAIMER

The above information is provided in good faith. Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.